


Doka formwork sheet 3-SO

Formwork & Scaffolding.
We make it work.

Data Sheet



96400-800

The Doka formwork sheet 3-SO is a high-grade 3-ply solid-wood sheet with urea-melamine resin coating on both sides, for horizontal and vertical formwork applications.

Sheet structure

- ÖNORM B 3023-compliant 3-ply solid-wood sheet made of spruce.
- The layers are crosswise glue-bonded.
- With/without all-round edge strip.

Glue-bonding

- Boil-resistant, alkali-resistant, water-resistant and weather-resistant.
- The glue-bonding is compliant with the requirements of Austrian standard ÖNORM B 3023.

Surfaces

- Both sides urea-melamine resin coating with approx. 130 g per m² and side.
- Edge sealing: Emulsion coating.

Technical data

Note:

All values in the tables are based on a sheet moisture content of 12 ± 3% on delivery. Changes in the wood's moisture content can have effects on the weight, dimensions and mechanical properties of the sheet.

The grain of the outside layers of this formwork sheet runs parallel to the longitudinal direction of the sheet.

Thickness and weight:

| Nominal thickness [mm] | Layers | Weight [kg/m ²] |
|------------------------|--------|-----------------------------|
| 21 | 3 | 9.7 |
| 27 | | 12.1 |

Formats:

| Length [cm] | Width [cm] |
|-------------|------------|
| 100 - 600 | 50 - 150 |

Format tolerances:

| | Tolerance |
|----------------------------|------------|
| Width | ± 1.0 mm |
| Length up to 3.0 m | ± 1.0 mm |
| Length 3.0 - 6.0 m | ± 1.5 mm |
| Perpendicularity | ± 1.0 mm/m |
| Straightness of sheet edge | ± 0,2 mm/m |

Mechanical properties (tested to EN 789):

| Nominal thickness [mm] | f _m [N/mm ²] | | EI [kNm ² /m] | |
|------------------------|-------------------------------------|---|--------------------------|---|
| | | ⊥ | | ⊥ |
| 21 | 30 | - | 7.2 | - |
| 27 | 25 | - | 14.0 | - |

f_m ... characteristic flexural strength
EI ... flexural stiffness
|| ... parallel to the grain
⊥ ... at right angles to the grain

- **Fire behaviour:** D - s2, d0
- **Thermal conductivity:** 0.13 W/mK
- **Formaldehyde class:** E1

Number of cycles

Possible frequency of use depends on many factors acting on the formwork sheet. Given optimum conditions of use and correct handling, up to **25 use cycles** (guide value) can be achieved.

Type of application and concreting results

The sheet has a 'low-absorbency' surface. Depending on the moisture penetration of the formwork sheet, its surface texture, i.e. the irregularities in the face layer (annual rings, knots etc.), imprints itself on the concrete, delivering uniform concrete faces with a slight wood texture.

The Doka formwork sheet 3-SO is a quality formwork sheet with selected wood quality that is used both in formwork systems and as loose sheets.

Note:

The sheets can be labelled with the client's name if desired.

Notes on use

Ensure that the formwork sheets are treated correctly whenever they are used.

Formwork sheets are subject to the natural swelling and shrinkage of wood associated with moisture absorption and loss in the corresponding climatic conditions.

- ▶ Prior to use, always make sure that the wood moisture content of the formwork sheets is matched to that of the surroundings.
- ▶ Cover sheets to protect them from extreme climatic influences such as exposure to sunlight or moisture. This reduces cracking.
- ▶ Seal cut edges, and around holes, with edge varnish.
- ▶ Use a high-quality release agent (e.g. Doka-Trenn or Doka-OptiX).
- ▶ Immediately after stripping the formwork, remove concrete residues from the surfaces that were in contact with the concrete.



NOTICE

Do not use pointed or sharp objects, wire brushes, abrasive disks or cup brushes.
Do not use high-pressure spray cleaners.

General information

The data stated here are guide values.

Note:

Follow the directions in the 'Formwork sheets' User Information booklet!

You can download it here:



www.doka.com/three-ply-sheets